

## PAVING BITUMEN 85/100

### DESCRIPTION:

Bitumen 85/100 is a standard Penetration Grade of Bitumen ASTM D 946M, typically used as a Paving Grade Bitumen suitable for road construction and for the production of asphalt pavements with superior properties particularly in road and airport constructions and other similar applications. This grade of Bitumen is mainly used in the manufacture of hot mix asphalt for bases and wearing courses. Penetration Grades of Bitumen is produced from Vacuum Residue, which is blown by hot air in the Biturox Blowing Unit; The fully automated process runs continuously resulting in a constant and homogeneous finished product quality. Visible vision Penetration Grade Bitumen can be supplied in any grade and are designated by two numbers to indicate the mid-points of their penetration ranges.

### PACKAGING:

Paving Bitumen is commonly packed in new steel drums, 150, 180 & 220 Kg barrels and Jumbo Bags or Flexi tank. Likewise, the rest of grades are ready to load Ex-work bulk Visible vision Bitumen by truck.

### CHARACTERISTICS AND SPECIFICATIONS:

Visible vision Bitumen guarantees that the Bitumen Grade 85/100 is produced in compliance and conformity to International Standards such as AASHTO M20-70 & ASTM D 946, also, meets the following specification requirements:



+97150 561 4588  
+97150 652 2362



visiblevision.io  
iinfo@visiblevision.io



Investment Park,  
092, Office 106, UAE

SPECIFICATIONS	UNIT	STANDARD	MIN	MAX
Penetration	dmm.	ASTM D 5	85	100
Softening Point	°C	ASTM D 36	42	49
Specific Gravity	g/cm <sup>3</sup>	ASTM D 70	1.01	1.06
Flash Point	°C	ASTM D 92	230	–
Solubility in Trichloroethylene	WT %	ASTM D 2042	99	–
<b>AFTER THIN-FILM OVEN TEST (TFOT) ASTM D 1754</b>				
Loss on Heating	WT %	ASTM D 6	–	1
Retained Penetration	%	ASTM D 5	47	–
Increase in Softening Point	°C	ASTM D 36	–	10
Spot Test	A.A.S.H.T.O.102		Negative	

