

PAVING GRADE 50/70

DESCRIPTION:

Bitumen 50/70 is a Penetration Grade of Bitumen according to the standard: BS EN 12591: 2009 typically used as a Paving Grade Bitumen suitable for road construction and to produce asphalt pavements with superior properties particularly in road and airport constructions and other similar applications. This grade of Bitumen is mainly used in the manufacture of hot mix asphalt for bases and wearing courses. Penetration Grades of Bitumen is produced from Vacuum Residue, which is blown by hot in the Biturox Blowing Unit; The fully automated process runs continuously resulting in a constant and homogeneous finished product quality. Visible vision Penetration Grade Bitumen can be supplied in any grade and are designated by two numbers to indicate the mid-points of their penetration ranges. The penetration grade bitumen has a thermoplastic property which causes the material to soften at high temperatures and to harden at lower temperatures. This unique temperature/ viscosity relationship is important when determining the performance parameters such as the adhesion, rheology, durability, and application temperatures of bitumen.

PACKAGING:

Paving Bitumen is commonly packed in new steel drums, 150, 180 & 220 Kg barrels and Jumbo Bags or Flexi tank. Likewise, the rest of grades are ready to load Ex-work bulk Visible vision Bitumen by truck.

CHARACTERISTICS AND SPECIFICATIONS:

Visible vision Bitumen guarantees that the Bitumen Grade 50/70 is produced in compliance and conformity to European Standards such BS EN 12591:2009. Also, it meets the following specification requirements:









SPECIFICATIONS	UNIT	STANDARD	MIN	MAX		
Penetration 25°C, 100g,5s	0.1 mm	EN 1426	50	70		
Softening Point	°C	EN 1427	46	54		
Flash Point	°C	EN ISO 2592	230	-		
Solubility in Trichloroethylene	%	EN 12592	99	-		
Penetration Index	-	ANNEX A b	-1.5	+0.7		
Dynamic Viscosity	Pa.s	EN 12596	145	-		
Fraass Breaking Point	°C	EN 12593	-	-8		
Kinematic Viscosity @ 135 °C	mm2 /s	EN 12595	295	-		
ROLLING THIN FILM OVEN TEST						
RESISTANCE TO HARDENING AT 163 °C						
Retained Penetration	-	EN 12607-1	50	-		







SPECIFICATIONS	UNIT	STANDARD	MIN	MAX
Increase in Softening Point	%	EN 12607-1	I	11
Change of Mass (Absolute Value)	°C		-	0.5



